

2-component adhesive can



Epoxy resin adhesive. For making waterproof resilient joints with fibrous concrete and fair-faced concrete plugs.

The components are colour-coded: component A is white component B is black

Mixing ratio 1:1

Test report as recommended by German KTW

Processing

Instructions for use:

Mixing time: until the adhesive is free from streaks

The surfaces being joined must be free from dust and grease

Pot life: 2 - 2.5 hours at +20°C, min. working temperature 8°C

Reaction temperature: 50-60°C

1 kg of adhesive is sufficient for approx. 40 concrete plugs MKK® B 15

1 kg of adhesive is sufficient for approx. 150 fibrous concrete plugs FB 22/50 mm